# **Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

## **Listing of Claims:**

1. (Currently Amended) A multilayer coating for a carbon-containing component comprising a protective coating, wherein the carbon-containing component includes graphite, amorphous carbon, carbon fibers, carbon-carbon composites, or a combination thereof; and

5

10

wherein the protective coating comprising comprises at least two layers, wherein each of said layers comprises a material selected from the group consisting of:

non-stoichiometric compounds of silicon and carbon; compounds of silicon, oxygen, and carbon; compounds of silicon, oxygen and nitrogen; compounds of silicon, nitrogen, and carbon; compounds of silicon, oxygen, nitrogen, and carbon; and silicon.

### 2-4. (Cancelled)

5. (Currently Amended) The <u>carbon-containing component</u> coating\_of claim 1, wherein the carbon-containing component comprises a carbon-carbon composite material said protective coating has a coefficient of thermal expansion which is less than the coefficient of thermal expansion of silicon carbide (SiC).

#### 6-9. (Cancelled)

- 10. (Currently Amended) The <u>carbon-containing component</u> coating of <u>claim 1</u> claim 5, wherein carbon-containing component comprises a plate-fin heat exchanger.
- 11. (Currently amended) The <u>carbon-containing component</u> coating of claim 1 wherein <u>said protective</u>—coating has a graded composition through its thickness.

### 12. (Canceled)

5

10

15

13. (Currently amended) A multilayer coating for a carbon-containing component comprising a protective coating, wherein the carbon-containing component includes graphite, amorphous carbon, carbon fibers, carbon-carbon composites, or a combination thereof; and

wherein the protective coating comprises comprising at least two layers, wherein each of said layers comprises a material selected from the group consisting of:

silicon (Si);

silicon carbide (SiC<sub>v</sub>); silicon oxycarbide (SiO<sub>x</sub>C<sub>v</sub>);

silicon oxynitride (SiO<sub>x</sub>N<sub>z</sub>);

silicon carbonitride (SiC<sub>v</sub>N<sub>z</sub>); and

silicon oxycarbonitride (SiO<sub>x</sub>C<sub>y</sub>N<sub>z</sub>);

wherein x < 2, y < 1 and z < 4/3, and at least one of x, y, and z is greater than zero, and wherein the coefficient of thermal expansion of said protective coating is less than the coefficient of thermal expansion of silicon carbide (SiC).

14-21. (Canceled)

22. (Currently Amended) A coating for a carbon-containing component comprising a protective coating, wherein the carbon-containing component includes graphite, amorphous carbon, carbon fibers, carbon-carbon composites, or a combination thereof; and

wherein said <u>protective</u> coating comprises at least one material selected from the group consisting of:

non-stoichiometric compounds of silicon and carbon; non-stoichiometric compounds of silicon and oxygen; non-stoichiometric compounds of silicon and nitrogen; compounds of silicon, oxygen, and carbon; compounds of silicon, oxygen, and nitrogen; compounds of silicon, nitrogen, and carbon; compounds of silicon, oxygen, nitrogen, and carbon; and silicon

----- wherein said carbon-containing component comprises a carbon-carbon composite material.

- 23. (Currently Amended) The <u>carbon-containing component of coating of claim 22</u>, wherein said <u>protective coating comprises</u> at least two layers, wherein each of said layers comprises a material selected from said group.
- 24. (Currently Amended) The <u>carbon-containing component</u> coating of claim 23, wherein each of said layers comprises a compound selected from the group consisting of silicon carbide (SiC<sub>y</sub>); silicon oxycarbide (SiO<sub>x</sub>C<sub>y</sub>); silicon carbonitride (SiC<sub>y</sub>N<sub>z</sub>); and silicon oxycarbonitride (SiO<sub>x</sub>C<sub>y</sub>N<sub>z</sub>), wherein x < 2, y < 1 and z < 4/3, and at least one of x, y, and z is greater than zero.

10

5

15

5

- 25. (Currently Amended) The <u>carbon-containing component</u> coating of claim 24, wherein <u>at least a portion of the carbon (C) in said compound of said layers is chemically bound.</u>
- 26. (Currently Amended) The <u>carbon-containing component</u> coating of claim 22, wherein said carbon-containing component comprises a plate-fin heat exchanger.
- 27. (Currently Amended) The <u>carbon-containing component</u> coating of claim 22, wherein said <u>protective</u> coating is applied directly to a surface of said carbon-containing component.
- 28. (New) The carbon-containing component of claim 22, wherein said protective coating has a coefficient of thermal expansion which is less than the coefficient of thermal expansion of silicon carbide (SiC).